

Product Description

Hybon™ 2026 roving from NEG is a continuous filament, single-end roving designed to reinforce polyester, vinyl ester, and epoxy resin systems in woven or multi-axial fabrics, pultrusion, and filament winding applications. Typical end-use applications include ladder rails, sucker rods, structural beams, angles, cable trays, pipe and storage tanks. Each package is in a wrap film with each pallet stretch wrapped to protect the fiber glass roving from dirt and moisture.

User Benefits

- High composite mechanical properties
- Multi-compatible with polyester, vinyl ester and epoxy resins.
- Rapid, complete and consistent wet out and saturation.
- Good abrasion resistance.
- Catenary free product.
- Supported by NEG’s extensive technical resources.
- Manufacturing facilities operate quality management systems that comply with ISO 9001:2015 requirements.
- Germanischer Lloyd (DNV GL) certified.

Type of Fiber	E-Glass (ASTM D 578-05, Section 4.2.2)					
Type of Sizing	Silane					
Roving Tex, nominal (g/km)	275	600	1200	1984	2400	4400
Roving Yield, nominal (yd/lb)	1800	827	413	250	206	113
Average Fiber Diameter (µm)	14	15	17	16	17	24
					24	
Other Tex/Yield options are available upon request.						

Storage

These products should be stored in a cool and dry area. Protect product from all sources of water at all times. A First-in-First-Out (FIFO) stock control system is recommended to minimize the influence of storage conditions. Prior to use, products should be conditioned in the work area for a minimum of 24 hours. If contents of a package unit are partially used, the unit should be closed until the next use. With proper storage, there are no known limitations on the shelf life of the product. To ensure optimal performance, retesting for mechanical properties and feeding behavior is recommended for products stored more than two years from the original production date. To avoid the possibility of potential injury, maintain column stability by limiting pallet stacking to two (2) high as noted on individual shipping containers.

More Information

<https://www.neg.co.jp/inquiry/>

<https://www.neg.co.jp/en/inquiry/>

NEG reserves the right to modify this document without prior notice.

NOTE: This data is offered for informational purposes only in the selection of a composite reinforcement.

Hybon™ is trademark of Electric Glass Fiber America, LLC.

Mechanical Properties

Impregnated Strand Tensile Testing

(ASTM D2343)

Tensile Strength (MPa/ksi) = 2790/405
Glass Content by Weight (%) = 57.9

Interlaminar Shear Strength (ASTM D2344)

Anhydride Cured Epoxy

Horizontal Shear Dry (MPa/ksi) = 71.7/10.4
Horizontal Shear Wet*(MPa/ksi) = 70.3/10.2
Strength Retention (%) = 98.0

Unsaturated Polyester

Horizontal Shear Dry (MPa/ksi) = 68.7/9.96
Horizontal Shear Wet*(MPa/ksi) = 60.6/8.79
Strength Retention (%) = 88.2
*6 Hour water boil conditioning

Packaging

- 48 packages/pallet
- 20 kg (44 lbs.) /package

