

## Product Description

**Hybon™ 2150** roving from NEG is made of E-Glass fiber and is compatible with epoxy resin systems. *HYBON 2150* roving is designed for woven or multi-axial knitting applications, which require good wet out and saturation together with good abrasion resistance and processing characteristics. *HYBON 2150* roving is supplied globally for woven or multi-axial fabrics, which are used in applications such as reinforcements for wind blades. Each package is in a wrap film with each pallet stretch wrapped to protect the fiber glass roving from dirt and moisture.

## User Benefits

- Compatible with epoxy resins.
- Hard strand tolerates difficult processing conditions without excessive filamentation.
- Single-end roving free from catenary.
- Fast wet out in thermoset resin systems.
- Consistent tex control and surface sizing system.
- Excellent package transfer efficiency through the use of an outer adhesive film.
- Manufacturing facilities operate quality management systems that comply with ISO 9001:2015 requirements.

Type of Fiber	E-Glass (ASTM D 578-05, Section 4.2.2)						
Type of Sizing	Silane						
Roving Tex, nominal (g/km)	275	300	600	900	1200	2400	4800
Roving Yield, nominal (yd/lb)	1800	1650	827	550	413	206	103
Average Fiber Diameter (µm)	14	14	15	15	17	17	24

Other Tex/Yield options are available upon request.

## Storage

These products should be stored in a cool and dry area. Protect product from all sources of water at all times. A First-in-First-Out (FIFO) stock control system is recommended to minimize the influence of storage conditions. Prior to use, products should be conditioned in the work area for a minimum of 24 hours. If contents of a package unit are partially used, the unit should be closed until the next use. With proper storage, there are no known limitations on the shelf life of the product. To ensure optimal performance, retesting for mechanical properties and feeding behavior is recommended for products stored more than two years from the original production date. To avoid the possibility of potential injury, maintain column stability by limiting pallet stacking to two (2) high as noted on individual shipping containers.

## More Information

<https://www.neg.co.jp/inquiry/>

<https://www.neg.co.jp/en/inquiry/>

NEG reserves the right to modify this document without prior notice.

**NOTE:** This data is offered for informational purposes only in the selection of a composite reinforcement.

Hybon™ is trademark of Electric Glass Fiber America, LLC.

## Mechanical Properties

### Impregnated Strand Tensile Testing

#### (ASTM D2343)

Tensile Strength (MPa/ksi) = 2555/370.6  
Glass Content by Weight (%) = 64.5

### Interlaminar Shear Strength (ASTM D2344)

#### Anhydride Cured Epoxy

Horizontal Shear Dry (MPa/ksi) = 71.7/10.4  
Horizontal Shear Wet\*(MPa/ksi) = 66.7/9.7  
Strength Retention (%) = 93.1  
Glass Content by Weight (%) = 60.9

\*6 Hour water boil conditioning

## Packaging

- 48 packages/pallet
- 20 kg (44 lbs.) /package